


Technical Data Sheet (TDS)

EHPC-60-ENF1
Polymerisations (PO)

EHPC-60-ENF1

Di-2-ethylhexyl peroxydicarbonate
CAS#16111-62-9
White (non-freezing) emulsion

Structural Formula



Description

Milky white emulsion, consisting of ca. 60 % Di-2-ethylhexyl peroxydicarbonate, desensitised with water and methanol. This branched, aliphatic peroxydicarbonate is used as a radical initiator for the polymerisation of monomers, mainly vinyl chloride (VCM).

Technical Data

Appearance	white emulsion
Desensitising agent	water / methanol
Assay	ca. 60 % w/w
Active oxygen (AO)	ca. 2.77 % w/w
Density at 20 °C	ca. 0.98 g/cm ³
Viscosity at 20 °C	ca. 200 mPa.s
Critical temperature (SADT)	ca. 5 °C
Cold storage stability	ca. -25 °C
Recommended storage temperature	-20 °C
Maximum transport temperature	-20 °C
Storage stability as from date of delivery	3 months

Standard Packaging

1100 kg in stainless steel IBC
25 kg in HDPE canister

Half-life Data

10 h / 1 h / 1 min (benzene, 0.1 mol/L) 41 °C / 57 °C / 90 °C

Technical Data Sheet (TDS)

EHPC-60-ENF1
Polymerisations (PO)



Application

VINYLCHLORIDE

Initiator for the polymerisation of VCM in suspension and micro suspension.

Temperature range: 45 - 60 °C

Usage level: 0.05 - 0.2 %

Advantages: liquid, therefore easy to dose and a high activity

A constant rate of polymerisation can be achieved in combination with other, thermally more stable peroxides (e.g. Dilauroylperoxide).

Further information on suitable initiators for the polymerisation of monomers is given in our application brochures on this subject.

Decomposition Products

Possible detectable decomposition products: carbon dioxide, 2-Ethylhexanol

Storage

Avoid any source of heat, light, humidity and protect the product from impurities. Keep within save temperature limits.

Disclaimer:

The information contained herein and all further technical advice that may be provided by United Initiators reflects our current knowledge and experience based on our internal research and development as to our products and applications. United Initiators does not make any warranties about the information provided as to specific properties of products described, their suitability for a particular application and representing complete instructions for use. Additionally, United Initiators does not make any warranties in respect of product and shelf life properties. We are not legally responsible and liable for the use of any information provided, including with regard to existing third party intellectual property rights, especially patent rights. We reserve the right to make any changes according to technological progress or further developments.

Application and usage of our products based on our technical advice is out of our control, strictly at your own risk and is the sole responsibility of the user. The user is not released from the obligation to conduct careful inspection and testing of incoming products in order to verify their suitability for the intended application.

United Initiators
Europe
T: +49 89 74422 237
F: +49 89 74422 6237
cs-initiators.eu@united-in.com

United Initiators
Nafta
T: +1 800 231 2702
F: +1 440 323 0898
cs-initiators.nafta@united-in.com

United Initiators
China
T: +86 20 6131 1370
F: +86 139 2503 8952
cs-initiators.cn@united-in.com

www.united-initiators.com