



Cumyl hydroperoxide CAS#80-15-9 Slightly yellow liquid

Structural Formula



Description

NOROX[®]CHM-50 is a solution of cumyl hydroperoxide in an accelerating phlegmatizer. NOROX[®]CHM-50 is a liquid polymerisation initiator for the room temperature cure of vinyl ester resins with the following advantages / properties.

- Moderate peak exotherm, typically lower than MEKPs
- Moderate gel time in vinyl ester resins
- Excellent final cure
- Low impurity levels (water, hydrogen peroxide, salts, etc.)
- No gas generation

Technical Data

Appearance	slightly yellow liquid
Active oxygen (AO)	approx. 4.5 % w/w
Density at 20 °C	approx. 1.04 g/cm ³
Flash point	approx. 60 °C
Critical temperature (SADT)	approx. 60 °C
Recommended storage temperature	max. 30 °C 🗢
Storage stability as from date of delivery	6 months

Standard Packaging

5 kg and 25 kg in HDPE canisters NAFTA: 8 lbs or 32 lbs in HDPE canisters



Application

NOROX[®]CHM-50 is an excellent liquid polymerisation initiator for the room temperature cure of epoxy vinyl ester resins (VER) when a curing reaction in a reasonable time without gassing is required. The Gel- and Peak time is longer compared to MEKP products (*e.g.* NOROX[®]ENP-102). However, the final cured resin hardness is often better than for resins initiated with MEKPs. After the curing, the residual styrene is typically lower compared to similar systems cured with MEKPS.

Decomposition Products

Possible detectable decomposition products: 2-phenyl-2-propanol, methane, acetophenone

Storage

Avoid any source of heat, light, humidity and protect the product from impurities. Keep within save temperature limits.



Measurements



Formulation (parts per weight)									
Resin		100	100	100	100	100	100		
NOROX [®] CHM-50	[Vol-%]	1.5	1.5	1.5	1.0	1.0	1.0		
Co/DMA Accelerator	[Vol-%]	1.0	0.5	0.2	1.0	0.5	0.2		
Curing Data									
Gel time 25 - 30 °C t _{gel}	[min]	4.2	6.6	15.0	4.3	7.9	22.2		
Gel time 25 - 35 °C t _{gel}	[min]	8.4	14.4	32.4	8.5	15.5	40.9		
Curing time t _{max}	[min]	22.2	37.7	82.8	22.2	37.1	86.4		
Peak temperature T _{max}	[°C]	138	134	95	137	133	94		

Disclaimer:

The information contained herein and all further technical advice that may be provided by United Initiators reflects our current knowledge and experience based on our internal research and development as to our products and applications. United Initiators does not make any warranties about the information provided as to specific properties of products described their suitability for a particular application and representing complete instructions for use. Additionally, United Initiators does not make any warranties in respect of product and shelf-life properties. We are not legally responsible and liable for the use of any information provided, including with regard to existing third-party intellectual property rights, especially patent rights. We reserve the right to make any changes according to technological progress or further developments. Abolication and usage of our products based on our technical advice is out of our control, strictly at your own risk and is the sole responsibility of the user. The user is not released from

Application and usage of our products based on our technical advice is out of our control, strictly at your own risk and is the sole responsibility of the user. The user is not released from the obligation to conduct careful inspection and testing of incoming products in order to verify their suitability for the intended application.

United Initiators **Europe** T: +49 89 74422 237 F: +49 89 74422 6237 <u>cs-initiators.eu@united-in.com</u> United Initiators

Nafta T: +1 800 231 2702 F. +1 440 323 0898 cs-initiators.nafta@united-in.com United Initiators **China** T: +86 21 6117 2760 F: +86 139 2503 8952 <u>cs-initiators.cn@united-in.com</u>

www.united-initiators.com