


TBPEH-30-AL

tert. Butyl-per-2-ethylhexanoate
CAS#3006-82-4
30%, solution in aliphatics
molar mass: 216.3 g/mol

Structural Formula



Description

Colourless, mobile liquid, consisting of app. 30% w/w tert. Butyl-per-2-ethyl hexanoate, desensitized with aliphatic hydrocarbons. This branched, aliphatic perester is used as an initiator (radical source) in the polymerisation of monomers (ethylene, methacrylates). The product is offered in IBC and bulk packaging.

Technical Data

Appearance	colourless liquid
Peroxide content	approx. 30 % w/w
Active oxygen	approx. 2.22 % w/w
De-sensitising agent	aliphatic
Density at 20 °C	approx. 0.79 g/cm ³
Viscosity at 20 °C	approx. 1.8 mPa•s
Refractive index at 20 °C	approx. 1.425
Critical temperature (SADT) in drums/IBC/Bulk	50 °C/40 °C/30 °C
Cold storage stability	to below -25 °C
Recommended storage temperature	max. 10 °C
Maximum transport temperature (drums/IBC/Bulk)	not specified/not specified/20 °C
Storage stability (activity) as from date of delivery	3 months

This product is in compliance with the Elektro G (EU-Directives: RoHS 2002/95/E G, WEEE 2002/96/EG)

Half-life Data

10h/1h/1min (0.1 m benzene): 74/92/130 °C

Application

ETHYLENE:

Initiator for the high pressure polymerisation of ethylene in combination with other peroxides of varying degrees of activity.

Temperature range: 160-210 °C.

Particular advantages: highly efficient; liquid, readily miscible with high-boiling aliphatics,

Transport: approved to be transported in intermediate bulk container (IBC, 1-1,25m³) and temperature controlled bulk tank containers (BTC, 19m³).

OTHER MONOMERS:

Initiator for the polymerisation of (meth-)acrylates and allyl monomers, where necessary in combination with more stable peresters (tert. Butylperoxy benzoate or tert. Butylperoxy-3,5,5-trimethyl hexanoate).

Temperature range: 80-120 °C.

Usage level: 0.3-3% as supplied.

Standard packaging

740kg plastics IBC

920kg stainless steel IBC

13to bulk container

Disclaimer

This information and all further technical advice are reflecting our present knowledge and experience based on internal tests with local raw materials with the purpose to inform about our products and applications. The information should not be construed as guaranteeing specific properties of products described or their suitability for a particular application, nor as providing complete instructions for use. The information implies no guarantee for product and shelf life properties, nor any liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. We reserve the right to make any changes according to technological progress or further developments.

Application and usage of our products based on our technical advice is out of our control and sole responsibility of the user. The user is not released from the obligation to conduct careful inspection and testing of incoming goods in order to verify the suitability for the intended application.

United Initiators
EU
T: +49 89 74422 237
F: +49 89 74422 6237
cs-initiators.eu@united-in.com

United Initiators
Nafta
T: +1 800 231 2702
F: +1 440 323 0898
cs-initiators.nafta@united-in.com

United Initiators
China
T: +86 20 6131 1370
F: +86 139 2503 8952
cs-initiators.cn@united-in.com

United Initiators
Australia
T: +61 2 9316 0046
F: +61 2 9316 0034
cs-initiators.au@united-in.com

www.united-initiators.com

Technical Data Sheet

